

Stock and service				
Germany	US	GB	France	International
DIN 1787	ASTM B 224	BS 6017	NF A 51-050 NF A51-108	ISO 431-1981 ISO 1337-1980
E-Cu 57	C11000/ETP	C 101/Cu-ETP-2	Cu al	Cu-EPT
E-Cu 58	C 10300/OXXLP	C 102/Cu OF	Cu-pl	Cu-HCP
SE-Cu	C 012200/DHP	C 106/Cu-DHP	Cu-bl	
SF-Cu	C 12000/DLP		Cu-b2	
CuZn5	B36,134,587,642 C 21000	2870/ 2875 CZ125	A51-101/103 CuZn 5	CuZn5
Cu Zn 10	B 36130,131,134 135,587 C 22000	CZ 101	CuZn10	Cu Zn 10
Cu Zn 15	B36,43,111,135, 359,587 C 23000	CZ 102	CuZn 15	CuZn 15
Cu Zn 20	B 36,134C 24000	CZ 103	Cu Zn20	Cu Zn 20
Cu Zn 28				
Cu Zn 30	B 19 36,134,135, 569,587 C 26000	CZ 106	Cu Zn 30	Cu Zn 30
Cu Zn 33	B 36, 587 C 26800	CZ 107	Cu Zn 33	Cu Zn 33
Cu Zn 36	B 36 134,135,587 C 27000		Cu Zn 36	
Cu Zn 37	B 36, 134,135,587 C 27400 C 27200	CZ 108		Cu Zn 37
Cu Zn 40	B111,135 C28000	CZ 109 Cu	Zn40 Cu	Zn 40
Cu Zn 36 Pb 1,5	B 453 C34500,C34700	CZ 119 CZ 118	Cz Zn 35 Pb2	Cu Zn 35 Pb2 Cu Zn 36 Pb 1
Cu Zn 37 Pb 0,5	C 34900,C 34800			
Cu Zn 36 Pb 3	B 16,121,453 C 36000,C 35600	CZ 124	Cu Zn 36 Pb 3	Cu Zn 36 Pb 3
Cu Zn 38 Pb 1,5	B 135 C 35300 C 37000	CZ 128	Cu Zn 38 Pb 2	Cu Zn 38 Pb 2
Cu Zn 39 Pb 0,5	B 171 C 36500	CZ 123		Cu Zn 40 Pb
Cu Zn 39 Pb 2	B 124 , 283 C 37700	CZ 120	Cu Zn 39 Pb 2	Cu Zn 39 Pb 2