

Stock and service				
Werkstoff-Nummer	Bezeichnung	UNS Nr.	ASTM	VD TÜV Werkstoffblatt und andere
2.4610	Hastelloy C4	N 06455	B 574/575	424
2.4602	Hastelloy C22	N 06022	B 574/575	479
2.4605	Alloy 59	N 06059	B 574*575	505
2.4606	Alloy 686	N 06686		
2.4819	Hastelloy C-276	N 10276	B 564/574/575	400 / DIN 17752
2.4617	Hastelloy B-3/B-4	N 10665	B 335/333	517
2.4603	Hastelloy G-30	N 06030	B 581	-
2.4619	Hastelloy G-3	N 06985	B 581	-
2.4066	Nickel 200	N 02200	B 160	DIN 17752/54
2.4068	Nickel 201	N 02201	B 160	345 / DIN 17752/54
1.4864	Incoloy DS	N 08330	B 511/512	
1.4876	Incoloy 800	N 08800	B 408/564	412
1.4876 H	Incoloy 800 H	N 08810	B 408/564	434
1.4876 HT	Incoloy 800 HT	N 08811	B 408/564	
2.4858	Incoloy 825	N 08825	B 425	432 / DIN 17752*54
2.4660	Alloy 20CB3	N 08020	B 462/463/472/473	
2.4816	Inconel 600	N 06600	B 166/168/564	305
2.4851	Inconel 601	N 06601	B 166/168	-
2.4663	Inconel 617	N 06617	B 166/168	485
2.4856	Inconel 625	N 06625	B 446/564/443	499
2.4642	Inconel 690	N 06690	B 166/168	-
2.4668	Inconel 718	N 07718	B 637 + WL	-
2.4669	Inconel X750	N 07750	B 637	-
2.4951	Nimonic 75	N 06075		WL + DIN 17752/54
2.4952	Nimonic 80A	N 07080	B 637	DIN 17240/480/754
2.4969	Nimonic 90	N 07090		WL + DIN 17754
2.4665	Hastelloy X	N 06602	B 572	WL
2.4650	Nimonic C 263	N 07263		WL
2.4360	Monel 400	N 04400	B 164/564	DIN 17754; 263
2.4375	Monel K 500	N 05500		DIN 17752/54
1.4562	Alloy 31	N 08031	B 549/564	509
1.4563	Alloy 28	N 08028	B 709 / EN 10088-3	SEW 400; 483
1.4565	Alloy 24		EN 10272	SEW 400
1.4529	X2 NiCrMoCu25 20 6	N 08925	B 649 / EN 10088-3	502
1.4539	X2 NiCrMoCu25 20 5	N 08904	B 649 / EN 10088-3	329/421
1.4980/4944	X5 NiCrTi26 15	S 66286	ASME-SA453	WL + 435
1.3912	Ni 36			SEW 385
1.3917	Ni 42			SEW 385
1.3922	Ni 48			
1.3981	NiCo29/18			
2.4973	Rene 41	N 07041	-	-
	weichmagnetische Eisen-Nickel-Legierungen			
3.7024/25	Titan Grade 1	N 50250	B 348; B 381	230
3.7034/35	Titan Grade 2	R 50400	B 348; B 381	230
3.7164/65	Titan Grade 5	R 56400	B 348; B 381	